

# Technical Information

## 12-20 | Bodyfiller Universal



### Process for coarse and fine bodyfiller

- High solids content; fast drying, easy to sand, good adhesion
- Universal body filler suitable for use on:
  - Steel
  - Galvanized steel
  - Aluminum
- Mix body filler and red hardener paste until homogeneous color

**Do not exceed 3% of hardener. Excess peroxide will cause discoloration in the finish**

## 1. Application

	<b>Mixing ratio</b>	100% by weight	12-20
		2 – 3% by weight	56-20
	<b>Potlife</b>	4 – 5 min. / 20°C	

## 2. Drying / sanding

	<b>Drying at 20°C</b>	20 – 30 min.
	<b>Infrared (short wave) (medium wave)</b>	4 min. 5 – 10 min.
	<b>Dry sanding Orbital sander</b>	P80 / P150 / P240

**Safety instructions: 2004/42/IIB(b) (250)180: The EU limit value for this product (product category: IIB.b) in ready to use form is max 250 g/l of VOC. The VOC content of this product is 180 g/l.**

**The products are suitable for professional use only.**

**It cannot be ruled out that this product contains particles < 0.1 µm**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 07/2017