

Technical Information




21-20 | Plastic Primer



1. Properties

- Adhesion primer for plastics ensures good adhesion of the following coats (filler, topcoat).

2. Application

	21-20 Plastic Primer shake vigorously for 2 min. before use
	Number of spray coats 1 – 2 Film thickness 5 µm
	Flash off at 20°C when applying 2 spray coats, 5 min. intermediate flash-off between the coats 15 min before primerfiller

3 Finishing

- Apply baslac 20-24/34/94 filler.
- Apply baslac 21-20 again when the flash-off time exceeds 30 min. at 20°C.

Safety instructions:

2004/42/IIB(e)(840)688: The EU limit value for this product (product category: IIB.e) in ready to use form is max 840 g/l of VOC. The VOC content of this product is 688 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 07/2017