

Technical Information

80-10 | Additive Flex



1. Properties

Plasticizing additive

- Use in plastics refinishing procedures, good elasticity and miscibility behaviour.

2. Application

	Mixing ratio	Undercoat materials: 100% by vol. 20-25% by vol. 80-10	Clears: 100% by vol. 40-25% by vol. 80-10
	Spray viscosity DIN 4 at 20°C	According undercoat TDS	According clear coat TDS
	Pot life		
	Spray gun	According undercoat TDS	According clear coat TDS
	Number of spray coats Film thickness	According undercoat TDS	According clear coat TDS

3. Drying

	Drying at 20°C at 60°C	According undercoat TDS	According clear coat TDS
	Infrared: (short wave) (medium wave)	According undercoat TDS	According clear coat TDS

Safety instructions:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 07/2017