

# 20-35



A brand of  
BASF - We create chemistry

20-35 variant 60-05

**Application** 60-05 Speeding Reducer in combination with baslac wet-on-wet primerfiller.

**Key Features**

- Reduction of drying times

**Remarks** No add of 60-05 Speeding Reducer in 2K Primerfiller/Filler at temperatures > 25°C possible, due to too short potlife.

**Mixing Ratio**

**3:1:1**



**Mixing Ratio**

100 % by volume

20-35 - 2K Primerfiller white



**Hardener**

33 % by volume

50-15 - 2K Hardener Fast  
50-20 - 2K Hardener normal



**Reducer**

33 % by volume

60-05 - Speeding Reducer

**Spray Viscosity**





**at 20°C**

DIN 4: 16-19 s

**Potlife at 20°C**

30 min

Application	 Compliant Gravity Spray Gun	 HVLP Spray Gun
Application Pressure	2 bar	
Nozzle Pressure		0.7 bar
Nozzle Size	1.3 -1.4	1.3
Number of Coats	2 (one on body-filled area and one on entire surface to be painted)	
Flash Off at 20°C	10 min	
Film thickness	20-35 µm	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

# 20-35

20-35 variant 60-05



A brand of  
BASF - We create chemistry

## Safety Advice

It cannot be ruled out that this product contains particles  $< 0.1 \mu\text{m}$ . The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

**2004/42/IIB(cii)(540)530:** The EU limit value for this product (product category: IIB.cii) in ready-for-use form is max 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany