

Technical Information

25-30



2K Primerfiller EP

Primerfiller

- Adhesion promoter with high corrosion protection
- High finish / appearance especially if forced dried

Application

	Mixing Ratio 4:1:2	100 % by volume	25-30
		25 % by volume	55-10
		50 % by volume	60-10, -20, -30
	Spray viscosity at 20°C	DIN 4: 18-20 s	
	Potlife at 20°C	8 h	
	HVLP spray gun		
	Nozzle size	1.6-1.8 mm	
	Application pressure	2 bar	
	Nozzle pressure	0.7 bar	
	Compliant gravity-feed spray gun		
	Nozzle Size	1.6-1.8 mm	
	Application Pressure	2 bar	
	Number of spraycoats	2	
	Film thickness	40-50 µm	

Safety advice:

2004/42/IIB(c1)(540)520: The EU limit value for this product (product category: IIB.c1) in ready to use form is max 540 g/l of VOC. The VOC content of this product is 520 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.


Technical Information

25-30





2K Primerfiller EP

Drying

	Drying at 20 °C	8 h
	Drying at 60 °C	30 min

Sanding

	Sanding manual, wet	P800
	Orbital sanding, dry	P400



Safety advice:

2004/42/IIB(c1)(540)520: The EU limit value for this product (product category: IIB.c1) in ready to use form is max 540 g/l of VOC. The VOC content of this product is 520 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.