# Technical Information 40-150



2K Standard Clear VOC

HS VOC clear for basecoat

High solids content, safe to spray, excellent flow and levelling, fast drying, good surface hardness and polishing behaviour.

## Application

	Mixing Ratio 2:1+10 %	100 % by volume	40-150	
		50 % by volume	50-150	
		10 % by volume	60-20	
<b>∏</b> ₅	Spray viscosity at 20°C		DIN 4: 17-19 s	
	Potlife at 20°C		2 h	
	HVLP spray gun			
> <b>-</b>	Nozzle size	1.3 mm		
	Application pressure	2 bar		
	Nozzle pressure	0.7 bar		
	Compliant gravity-feed spray gun	,		
	Nozzle Size		1.3-1.4 mm	
	Application Pressure		2 bar	
<b>X</b>	Number of spray coats	2		
	Film thickness		40-60 µm	
<u>/†/†/</u>	Flash off at 20°C	3 min between spray coats		
		<u> </u>		

#### Safety advice:

The GB24409-2020 published by China Standardization Administration limit value for this product in ready to use form is max 480 g/litre of VOC. The VOC content of this product is 479 g/litre. The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1  $\mu$ m.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany,

# Technical Information 40-150



2K Standard Clear VOC

## Drying

$\bigcirc$	Drying at 20°C	16 h
	Drying at 60°C	30 min
R	Infrared (short wave)	8 min
	Infrared (medium wave)	10-15 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



### Safety advice:

The GB24409-2020 published by China Standardization Administration limit value for this product in ready to use form is max 480 g/litre of VOC. The VOC content of this product is 479 g/litre. The products are suitable for professional use only.

#### It cannot be ruled out that this product contains particles < 0.1 $\mu$ m.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany,