Technical Information 40-22



40-22 2K Clear

2K Clear coat

MS clear with broad usage for everyday-repairs

High robustness

Application

		Mixing Ratio 2:1+10 %	100 % by volume	40-22	
			50 % by volume	50-20	
			10 % by volume	60-10, -20	
Г	s	Spray viscosity at 20°C		DIN 4: 13-16 s	
		Potlife at 20°C		3 h	
		HVLP spray gun			
	÷	Nozzle size	1.3		
		Nozzle pressure	0.7 bar		
* 7		Compliant gravity-feed spray gun	,		
		Nozzle Size		1.3-1.4	
		Application Pressure	2 bar		
g	E	Number of spray coats		2 - 3	
	π	Film thickness	50 - 60 μm		
<u>}</u>) †/ ≅©	Flash off at 20°C	Ę	ō min between each spray coat	
		Application Remark	Use the	e 60-10 or 60-20 reducer, if required.	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 $\mu m.$

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany,

Technical Information 40-22



40-22 2K Clear

Drying

	Drying at 20°C	5 h
\bigcirc	Drying at 60°C	30 min
	Infrared (short wave)	8 min
ìR	Infrared (medium wave)	10-15 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only. It cannot be ruled out that this product contains particles < $0.1 \,\mu$ m.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany,