








Technical Information

Chart 2



Pre-treatment of substrates and old paintwork







Bare steel and aluminium repair

Cleaning / sanding	70-10 Silicone Remover		1x		wipe dry	70-10 Silicone Remover		1x		wipe dry	P80-P150		70-10 Silicone Remover		1x
															wipe dry

New panels (factory primed)

Cleaning / sanding	70-10 Silicone Remover		1x		wipe dry		P 240-P 320	70-10 Silicone Remover		1x		wipe dry
--------------------	------------------------	---	----	---	----------	---	-------------	------------------------	---	----	---	----------

Plastics and GRP / SMC

Plastics	70-20 Cleaner Plastic		1x		damaged area: P 80-P 600 entire part: sanding pad	70-20 Cleaner Plastic		1x		wipe dry	Heating PU foam and polyamide (PA) must be heated for 1 hour at 60°C to remove mould release agents and water		1 h at 60°C		1x moistened cloth
----------	-----------------------	---	----	---	--	-----------------------	---	----	---	----------	--	---	-------------	---	-----------------------

GRP / SMC	70-20 Cleaner Plastic		1x		wipe dry		P 180-240	70-20 Cleaner Plastic		1x		wipe dry
-----------	-----------------------	---	----	---	----------	---	-----------	-----------------------	---	----	---	----------

Safety instructions:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 04/2021