

# Technical Information

## 30 Line CV



### 30- CV Topcoat

HS – VOC – compliant 1 stage solid topcoat

- Easy application combined with good hiding power
- Suitable for large areas / surfaces with very good appearance and flow.
- Excellent UV resistance and fast drying

## Application

	<b>Mixing Ratio</b>	100 % by volume	
		50 % by volume	51-515, -520 (stir well)
	<b>Spray viscosity at 20°C</b>		DIN 4: 20-24 s
	<b>Potlife at 20°C</b>		2 h
	<b>HVLP spray gun</b>		
	Nozzle size		1.5 mm
	Application pressure		2 bar
	Nozzle pressure		0.7 bar
	<b>Compliant gravity-feed spray gun</b>		
	Nozzle Size		1.4 mm
	Application Pressure		2 bar
	<b>Number of spray coats</b>		
	<b>Film thickness</b>		50-70 µm
	<b>Application Remark</b>	Airless/ airmix: 0,23 – 0,28mm, 120-180 bar / + max 2 bar atomization air	

### Safety advice:

**2004/42/IIIB(d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.


# Technical Information

## 30 Line CV



30- CV Topcoat

### Drying

		51-520	51-515
	<b>Drying at 20°C</b>	8 h	6 h
	<b>Drying at 60°C</b>	30 min	25 min

Please note: For automotive refinishing, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



#### Safety advice:

**2004/42/IIIB(d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.