

Technical Information

40-40



40-40 variant 80-10

Plasticizing additive 80-10, use for flexible refinish procedures.

- good elasticity
- good miscibility behaviour

Application

| | | | |
|----------------------|---|-------------------------------|----------------------|
| | Mixing Ratio PreMix | 100 % by volume | 40-40 |
| | | 25 % by volume | 80-10 |
| | Mixing Ratio 2:1+10 % | 100 % by volume | PreMix |
| | | 50 % by volume | 50-20, -30 |
| | | 10 % | 60-10, -20, -30, -40 |
| | Spray viscosity at 20°C | DIN 4: 16 s | |
| | Potlife at 20°C | 4 h | |
| | HVLP spray gun | | |
| | Nozzle size | 1.3 mm | |
| | Application pressure | 2 bar | |
| | Nozzle pressure | 0.7 bar | |
| | Compliant gravity-feed spray gun | | |
| Nozzle Size | 1.3-1.4 mm | | |
| Application Pressure | 2 bar | | |
| | Number of spray coats | 2 | |
| | Film thickness | 50-70 µm | |
| | Flash off at 20°C | 2-3 min after each spray coat | |

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Technical Information

40-40



40-40 variant 80-10

Drying

| | | |
|---|------------------------|-----------|
|  | Drying at 20°C | 8 h |
| | Drying at 60°C | 30 min |
|  | Infrared (short wave) | 8 min |
| | Infrared (medium wave) | 10-15 min |

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.