

Información Técnica

Parte 2



Pre-tratamiento de sustratos y pintura antigua

Reparación de acero desnudo y aluminio

Limpieza / lijado	70-10 Eliminador de Silicona			70-10 Eliminador de Silicona				70-10 Eliminador de Silicona		
		1x	secar con paño		1x	secar con paño			P80/P150	1x

Piezas nuevas (imprimadas de fábrica)

Limpieza / lijado	70-10 Eliminador de Silicona				70-10 Eliminador de Silicona		
		1x	secar con paño			P240/P320	1x

Plásticos

Plásticos	70-20 Limpiador de plásticos			70-20 Limpiador de plásticos			Calentamiento Espuma de PU y poliamida (PA) se deben calentar durante 1 hora a 60°C para eliminar agentes desmoldantes y agua		
		1x	damaged area: P80-P600 entire part: sanding pad		1x	secar con paño		1 h 60°C	1x moistened cloth

GRP / SMC

GRP / SMC	70-20 Limpiador de plásticos				70-20 Limpiador de plásticos		
		1x	secar con paño			P180/P240	1x

Aviso de Seguridad:

Estos productos son aptos únicamente para uso profesional.

No se puede descartar que este producto contenga partículas de menos de 0,1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany 05/2024