

Technical Information

Chart 2



Предварительная подготовка различных подложек и старого ЛКП

Голый металл и алюминий

Очистка / шлифовка	70-10 Очиститель силикона			70-10 Очиститель силикона			P80-P150	70-10 Очиститель силикона	
		1x	Вытереть насухо		1x	Вытереть насухо			1x
									Вытереть насухо

Новые детали (загрунтованные на заводе)

Очистка / шлифовка	70-10 Очиститель силикона				70-10 Очиститель силикона		
		1x	Вытереть насухо	P 240-P 320		1x	Вытереть насухо

Пластик и GRP / SMC

Пластики	70-20 Очиститель для пластика			70-20 Очиститель для пластика			Нагрев Вспененные полиуретаны PU и полиамиды (PA) должны быть нагреты на протяжении 1 часа при 60°C для удаления смазки от		
		1x	Зона повреждения : P 80-P 600 вся деталь: шлифовальная губка		1x	Вытереть насухо		1 ч при 60°C	1x Смоченной салфеткой

GRP / SMC	70-20 Очиститель для пластика				70-20 Очиститель для пластика		
		1x	Вытереть насухо	P 180-240		1x	вытереть

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 04/2021

Technical Information

Chart 2



Техника безопасности:

Продукт предназначен для профессионального применения.

Продукт может содержать частицы размером < 0.1 мкм.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany, 04/2021